

# UN38.3 测试报告

## UN38.3 Test Report

Sample Description  
& Model

Li-ion Battery pack B7-1-26-26-1C-II  
(25.9V 2.6Ah 67Wh)

Applicant

FOSHAN Shunde Xinshengyuan Electrical Appliances  
Co., Ltd./FOSHAN NAIBAO ELECTRIC CO., LTD./  
XPOWER MANUFACTURE,INC.

Manufacturer

JiangXi DBK Co.Ltd

P O N Y 谱 尼 测 试  
Pony Testing International Group  
[www.ponytest.com](http://www.ponytest.com)



No.: MOIPCGLT20223721  
Code: 5i2g9czfp7

## I、SAMPLE DESCRIPTION

Sample description		Li-ion Battery pack		Sample model	B7-1-26-26-1C-I1	
Applicant		FOSHAN Shunde Xinshengyuan Electrical Appliances Co., Ltd./FOSHAN NAIBAO ELECTRIC CO., LTD./ XPOWER MANUFACTURE,INC.				
Manufacturer	Name	JiangXi DBK Co.Ltd				
	Address	High Tech Industrial Park Fuzhou,JiangXi,China				
	Tel	86-757-23378438				
	E-mail	lgq8757@163.com		Web	---	
Nominal voltage		25.9V	Rated capacity	2.6Ah	Limited charge voltage	29.4V
Charge current		1A	Maximum continuous charge current	2.6A	End charge current	0.052A
Cut-off voltage		20.3V	Maximum discharge current	10A	Mass	372.863g
Cell number		7PCS	Cell model	18650	Cell capacity	2.6Ah
Manufacturer of cell		JiangXi DBK Co.Ltd				
Electrochemistry System		LiNiCoMnO2				
Entrust date		2020-04-16		Finished date	2020-05-20	

## II、TEST METHOD

UNITED NATIONS “Recommendations on the TRANSPORT OF DANGEROUS GOODS” Manual of Tests and Criteria (ST/SG/AC.10/11/Rev.6/Amend.1), Part III sub-section.

## III、TEST ITEM & CONCLUSION

ITEM	SAMPLE NUMBER	STANDARD	CONCLUSION
Altitude simulation	N1~N4 C1~C4	UN38.3 ST/SG/AC.10/11/Rev.6/ Amend.1	PASS
Thermal test			PASS
Vibration			PASS
Shock			PASS
External short circuit			PASS
Impact	N5~N9 C5~C9		PASS
Overcharge	N1~N4 C1~C4		PASS
Forced discharge	N10~N19 C10~C19		PASS

The Samples has passed the test items of UNITED NATIONS “Recommendations on the TRANSPORT OF DANGEROUS GOODS” Manual of Tests and Criteria (ST/SG/AC.10/11/Rev.6/Amend.1), Part III sub-section.

Appraiser:

Checker:

Approver:

Issue Date: 2020-05-20



**Notes:**

N1~N4: Batteries at first cycle in fully charged states;

N5~N9: Cells at first cycle at 50% of the design rated capacity;

N10~N19: Cells at first cycle in fully discharged states;

C1~C4: Batteries after 25 cycles ending in fully charged states;

C5~C9: Cells after 25 cycles at 50% of the design rated capacity;

C10~C19: Cells after 25 cycles ending in fully discharged states.

**IV、PHOTO OF THE SAMPLE**

Sample No.: T20223721



Authenticate the photo on original report only

## V、TEST METHOD

Tests T.1 to T.5 shall be conducted in sequence on the same cell or battery. Tests T.6 and T.8 shall be conducted using not otherwise tested cells or batteries. Test T.7 may be conducted using undamaged batteries previously used in tests T.1 to T.5 for purposes of testing on cycled batteries.

In order to quantify the mass loss, the following procedure is provided:

$$\text{Mass loss}(\%) = (M_1 - M_2) / M_1 \times 100$$

Where  $M_1$  is the mass before the test and  $M_2$  is the mass after the test. When mass loss does not exceed the values in Table below, it shall be considered as “no mass loss”.

Mass M of cell or battery	Mass loss limit
$M < 1\text{g}$	0.5%
$1\text{g} \leq M \leq 75\text{g}$	0.2%
$M > 75\text{g}$	0.1%

### T.1 Altitude simulation

Test cells and batteries shall be stored at a pressure of 11.6 kPa or less for at least six hours at ambient temperature ( $20 \pm 5^\circ\text{C}$ ).

Cells and batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.

### T.2 Thermal test

Test cells and batteries are to be stored for at least six hours at a test temperature equal to  $72 \pm 2^\circ\text{C}$ , followed by storage for at least six hours at a test temperature equal to  $-40 \pm 2^\circ\text{C}$ . The maximum time interval between test temperature extremes is 30 minutes. This procedure is to be repeated until 10 total cycles are complete, after which all test cells and batteries are to be stored for 24 hours at ambient temperature ( $20 \pm 5^\circ\text{C}$ ). For large cells and batteries the duration of exposure to the test temperature extremes should be at least 12 hours.

Cells and batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.



### T.3 Vibration

Cells and batteries are firmly secured to the platform of the vibration machine without distorting the cells in such a manner as to faithfully transmit the vibration. The vibration shall be a sinusoidal waveform with a logarithmic sweep between 7 Hz and 200 Hz and back to 7 Hz traversed in 15 minutes. This cycle shall be repeated 12 times for a total of 3 hours for each of three mutually perpendicular mounting positions of the cell. One of the directions of vibration must be perpendicular to the terminal face.

The logarithmic frequency sweep shall differ for cells and batteries with a gross mass of not more than 12 kg (cells and small batteries), and for batteries with a gross mass of more than 12 kg (large batteries).

For cells and small batteries: from 7 Hz a peak acceleration of 1  $g_n$  is maintained until 18 Hz is reached. The amplitude is then maintained at 0.8 mm (1.6 mm total excursion) and the frequency increased until a peak acceleration of 8  $g_n$  occurs (approximately 50 Hz).

A peak acceleration of 8  $g_n$  is then maintained until the frequency is increased to 200 Hz.

For large batteries: from 7 Hz to a peak acceleration of 1  $g_n$  is maintained until 18 Hz is reached. The amplitude is then maintained at 0.8 mm (1.6 mm total excursion) and the frequency increased until a peak acceleration of 2  $g_n$  occurs (approximately 25 Hz). A peak acceleration of 2  $g_n$  is then maintained until the frequency is increased to 200 Hz.

Cells and batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire during the test and after the test and if the open circuit voltage of each test cell or battery after testing in its perpendicular mounting position is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.

### T.4 Shock

Test cells and batteries shall be secured to the testing machine by means of a rigid mount which will support all mounting surfaces of each test battery.

Each cell shall be subjected to a half-sine shock of peak acceleration of 150  $g_n$  and pulse duration of 6 milliseconds. Alternatively, large cells may be subjected to a half-sine shock of peak acceleration of 50  $g_n$  and pulse duration of 11 milliseconds.

Each battery shall be subjected to a half-sine shock of peak acceleration depending on the mass of the battery. The pulse duration shall be 6 milliseconds for small batteries and 11 milliseconds for large batteries. The formulas below are provided to calculate the appropriate minimum peak accelerations.

Battery	Minimum peak acceleration	Pulse duration
Small batteries	<p>150 g<sub>n</sub> or result of formula</p> $\text{Acceleration}(g_n) = \sqrt{\left(\frac{100850}{\text{mass}^*}\right)}$ <p>Whichever is smaller</p>	6 ms
Large batteries	<p>50 g<sub>n</sub> or result of formula</p> $\text{Acceleration}(g_n) = \sqrt{\left(\frac{30000}{\text{mass}^*}\right)}$ <p>Whichever is smaller</p>	11 ms

\* Mass is expressed in kilograms.

Each cell or battery shall be subjected to three shocks in the positive direction and to three shocks in the negative direction in each of three mutually perpendicular mounting positions of the cell or battery for a total of 18 shocks.

Cells and batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.

#### T.5 External short circuit

The cell or battery to be tested shall be heated for a period of time necessary to reach a homogeneous stabilized temperature of  $57 \pm 4^\circ\text{C}$ , measured on the external case. This period of time depends on the size and design of the cell or battery and should be assessed and documented. If this assessment is not feasible, the exposure time shall be at least 6 hours for small cells and small batteries, and 12 hours for large cells and large batteries. Then the cell or battery at  $57 \pm 4^\circ\text{C}$  shall be subjected to one short circuit condition with a total external resistance of less than 0.1 ohm. This short circuit condition is continued for at least one hour after the cell or battery external case temperature has returned to  $57 \pm 4^\circ\text{C}$ , or in the case of the large batteries, has decreased by half of the maximum temperature increase observed during the test and remains below that value. The short circuit and cooling down phases shall be conducted at least at ambient temperature.

Cells and batteries meet this requirement if their external temperature does not exceed  $170^\circ\text{C}$  and there is no disassembly, no rupture and no fire during the test and within six hours after the test.



#### T.6 Impact / Crush

Impact (applicable to cylindrical cells not less than 18 mm in diameter)

The test sample cell or component cell is to be placed on a flat smooth surface. A  $15.8 \text{ mm} \pm 0.1 \text{ mm}$  diameter, at least 6 cm long, or the longest dimension of the cell, whichever is greater, Type 316 stainless steel bar is to be placed across the centre of the sample. A  $9.1 \text{ kg} \pm 0.1 \text{ kg}$  mass is to be dropped from a height of  $61 \pm 2.5 \text{ cm}$  at the intersection of the bar and sample in a controlled manner using a near frictionless, vertical sliding track or channel with minimal drag on the falling mass. The vertical track or channel used to guide the falling mass shall be oriented 90 degrees from the horizontal supporting surface.

The test sample is to be impacted with its longitudinal axis parallel to the flat surface and perpendicular to the longitudinal axis of the  $15.8 \text{ mm} \pm 0.1 \text{ mm}$  diameter curved surface lying across the centre of the test sample. Each sample is to be subjected to only a single impact.

Crush (applicable to prismatic, pouch, coin/button cells and cylindrical cells less than 18 mm in diameter)

A cell or component cell is to be crushed between two flat surfaces. The crushing is to be gradual with a speed of approximately 1.5 cm/s at the first point of contact. The crushing is to be continued until the first of the three options below is reached.

- (a) The applied force reaches  $13 \text{ kN} \pm 0.78 \text{ kN}$ ;
- (b) The voltage of the cell drops by at least 100 mV; or
- (c) The cell is deformed by 50% or more of its original thickness.

Once the maximum pressure has been obtained, the voltage drops by 100 mV or more, or the cell is deformed by at least 50% of its original thickness, the pressure shall be released.

A prismatic or pouch cell shall be crushed by applying the force to the widest side. A button/coin cell shall be crushed by applying the force on its flat surfaces. For cylindrical cells, the crush force shall be applied perpendicular to the longitudinal axis.

Each test cell or component cell is to be subjected to one crush only. The test sample shall be observed for a further 6 h. The test shall be conducted using test cells or component cells that have not previously been subjected to other tests.

Cells and component cells meet this requirement if their external temperature does not exceed  $170^\circ \text{C}$  and there is no disassembly and no fire during the test and within six hours after this test.

#### T.7 Overcharge

The charge current shall be twice the manufacturer's recommended maximum continuous charge current. The minimum voltage of the test shall be as follows:

- (a) When the manufacturer's recommended charge voltage is not more than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage of the battery or 22V.
- (b) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage.

Tests are to be conducted at ambient temperature; the duration of the test shall be 24 hours.

Rechargeable batteries meet this requirement if there is no disassembly and no fire during the test and within seven days after the test.

#### T.8 Forced discharge


Each cell shall be forced discharged at ambient temperature by connecting it in series with a 12V D.C. power supply at an initial current equal to the maximum discharge current specified by the manufacturer.

The specified discharge current is to be obtained by connecting a resistive load of the appropriate size and rating in series with the test cell. Each cell shall be forced discharged for a time interval (in hours) equal to its rated capacity divided by the initial test current (in ampere).

Primary or rechargeable cells meet this requirement if there is no disassembly and no fire during the test and within seven days after the test.



## VI、TEST PROCEDURE



## VII、TEST APPARATUS

IE-0121 High precision battery test system

IE-0514 High precision battery test instrument

IE-0434 Vacuum drying oven

IE-0090 Multimeter

IE-0824 Tableland air pressure gauge

IE-0219 Rapid temperature change test chamber

IE-0281 Temperature controlled short circuit testing machine

IE-0503 Electric vibration test system

IE-0259 Electronic balance

IE-0287 Vertical impact crash test platform

IE-0833 Battery heavy shock testing machine

IE-0185 The digital thermometer (TC)

IE-0294 Programmable DC power source

## VIII、 DATA

### 1. Altitude simulation

No.	Pre-test		After test		Mass loss (%)	Voltage loss (%)	Whether leakage, venting, disassembly, rupture, fire (Y/N)
	Mass (g)	Voltage (V)	Mass (g)	Voltage (V)			
N1	372.313	29.27	372.289	29.25	0.006	0.068	N
N2	373.680	29.30	373.652	29.27	0.007	0.102	N
N3	373.438	29.35	373.422	29.31	0.004	0.136	N
N4	372.965	29.32	372.935	29.28	0.008	0.136	N
C1	373.640	29.30	373.638	29.28	0.001	0.068	N
C2	373.617	29.30	373.602	29.27	0.004	0.102	N
C3	369.662	29.29	369.634	29.26	0.008	0.102	N
C4	372.863	29.28	372.844	29.25	0.005	0.102	N

### 2. Thermal test

No.	Pre-test		After test		Mass loss (%)	Voltage loss (%)	Whether leakage, venting, disassembly, rupture, fire (Y/N)
	Mass (g)	Voltage (V)	Mass (g)	Voltage (V)			
N1	372.289	29.25	372.093	28.72	0.053	1.812	N
N2	373.652	29.27	373.486	28.71	0.044	1.913	N
N3	373.422	29.31	373.223	28.72	0.053	2.013	N
N4	372.935	29.28	372.768	28.72	0.045	1.913	N
C1	373.638	29.28	373.496	28.77	0.038	1.742	N
C2	373.602	29.27	373.499	28.75	0.028	1.777	N
C3	369.634	29.26	369.473	28.73	0.044	1.811	N
C4	372.844	29.25	372.693	28.75	0.040	1.709	N



### 3. Vibration

No.	Pre-test		After test		Mass loss (%)	Voltage loss (%)	Whether leakage, venting, disassembly, rupture, fire (Y/N)
	Mass (g)	Voltage (V)	Mass (g)	Voltage (V)			
N1	372.093	28.72	372.093	28.72	0.000	0.000	N
N2	373.486	28.71	373.486	28.71	0.000	0.000	N
N3	373.223	28.72	373.221	28.72	0.001	0.000	N
N4	372.768	28.72	372.768	28.71	0.000	0.035	N
C1	373.496	28.77	373.493	28.77	0.001	0.000	N
C2	373.499	28.75	373.499	28.74	0.000	0.035	N
C3	369.473	28.73	369.472	28.73	0.000	0.000	N
C4	372.693	28.75	372.693	28.75	0.000	0.000	N

### 4. Shock

No.	Pre-test		After test		Mass loss (%)	Voltage loss (%)	Whether leakage, venting, disassembly, rupture, fire (Y/N)
	Mass (g)	Voltage (V)	Mass (g)	Voltage (V)			
N1	372.093	28.72	372.092	28.72	0.000	0.000	N
N2	373.486	28.71	373.486	28.71	0.000	0.000	N
N3	373.221	28.72	373.221	28.71	0.000	0.035	N
N4	372.768	28.71	372.766	28.71	0.001	0.000	N
C1	373.493	28.77	373.493	28.77	0.000	0.000	N
C2	373.499	28.74	373.497	28.73	0.001	0.035	N
C3	369.472	28.73	369.472	28.73	0.000	0.000	N
C4	372.693	28.75	372.693	28.75	0.000	0.000	N

#### 5. External short circuit

No.	Peak temperature ( °C)	Whether disassembly, rupture, fire (Y/N)
N1	57.3	N
N2	57.3	N
N3	57.6	N
N4	57.5	N
C1	57.6	N
C2	57.3	N
C3	57.6	N
C4	57.6	N

#### 6. Impact

No.	Peak temperature ( °C)	Whether disassembly, fire (Y/N)
N5	96.5	N
N6	95.7	N
N7	96.8	N
N8	92.3	N
N9	97.4	N
C5	98.5	N
C6	97.7	N
C7	93.6	N
C8	95.1	N
C9	94.2	N



7. Overcharge

No.	Whether disassembly, fire (Y/N)
N1	N
N2	N
N3	N
N4	N
C1	N
C2	N
C3	N
C4	N

8. Forced discharge

No.	Whether disassembly, fire (Y/N)
N10	N
N11	N
N12	N
N13	N
N14	N
N15	N
N16	N
N17	N
N18	N
N19	N
C10	N
C11	N
C12	N
C13	N
C14	N
C15	N
C16	N
C17	N
C18	N
C19	

\*\*\* End of report \*\*\*