





中国认可 国际互认 TESTING **CNAS L4065**



Report No.: GZLS20190911U01

TEST REPORT

检测报告

NAME OF SAMPLE

产品名称

Model and parameters

型号参数

CLASSIFICATION OF TEST

检测类别

Issue Date

签发日期

Rechargeable Li-ion Battery Pack

可充式锂离子电池组

P1089503-003 7.2V 3400mAh 24.48Wh

Commission test

委托检测

2019.10.08

测试 Tested by	审核 Reviewed by	批准 Approved by
Runkay Ye Test Engineer	Audit Engineen	Hongton Xu Approval Engineer

广州邦禾检测技术有限公司

Guangzhou MCM Certification & Testing Co., Ltd.





	Test Information 测试信息						
Application/申请单位:							
Applicant 申请单位	TWS Technology (Guangzhou) Limited 广州明美新能源有限公司						
Address 申请单位地址	No.39 Nanyunsan Road, Science Park, Hi-Tech Industrial Development Zone, Guangzhou 510663,P.R.China 广州市高新技术产业开发区科学城南云三路 39 号						
Contact information 联系方式	Tel: +86-20-29114223 Fax: +86-20-22215113 E-mail: li.jun@tws.com						
General information/基本	信息: 15-12 1-12 1-12 1-12 1-12 1-12 1-12 1-1						
Test item description 产品名称	Rechargeable Li-ion Battery Pack 可充式锂离子电池组						
Classification 产品分类	□ Primary□ Cell (single cell battery)□ Battery						
Trade Mark 商标名称	_						
Model and parameters 型号参数	P1089503-003 7.2V 3400mAh 24.48Wh						
Manufacturer 制造单位	TWS Technology (Guangzhou) Limited 广州明美新能源有限公司						
Address 制造单位地址	No.39 Nanyunsan Road, Science Park, Hi-Tech Industrial Development Zone, Guangzhou 510663,P.R.China 广州市高新技术产业开发区科学城南云三路 39 号						
Factory 生产单位	TWS Technology (Guangzhou) Limited 广州明美新能源有限公司						
Address 生产单位地址	No.39 Nanyunsan Road, Science Park, Hi-Tech Industrial Development Zone, Guangzhou 510663,P.R.China						
Testing laboratory/测试实	验室:						
Laboratory 测试单位	Guangzhou MCM Certification & Testing Co., Ltd. 广州邦禾检测技术有限公司						
Address 测试单位地址	1 F No.13, Zhong San Section, ShiGuang Road, Panyu District, Guangzhou City, Guangdong Province, China. 中国 广州市番禺区市广路钟三路段 13 号之一						
Testing Location 测试实验室地址	As above 同上						
Test Specification/测试标	准:						
Standard 测试标准	UN Manual of Tests and Criteria ST/SG/AC.10/11/Rev.6, amend1, section 38.3. 联合国《关于危险货物运输的建议书试验和标准手册》 ST/SG/AC.10/11/Rev.6, amend1, section 38.3.						
Procedure deviation 过程偏差	□ None □ 38.3.3 (f) □ 38.3.3 (g)						
Receiving Date 样品接收日期 2019.09.11							



General product information 一般产品信息:

This battery is constructed with 2 lithium-ion cells (2S1P) and have overcharge, over-discharge, over current and short-circuits proof circuit, covered with black hard glue case.

电池由2个电芯(2串1并)组成,含有过充、过放、过流和短路的保护线路,覆盖着黑色硬胶外壳。

Label 标签:



32417BKT0154RB

MFD(生產日期/生产日期): 20171121

Technology Information 技术参数:

Model 型号	Nominal Capacity 额定容量	Nominal Voltage 额定电压	Nominal Charge Current 额定充电 电流	Nominal Discharge Current 额定放电 电流	Maximum Charge Current 最大充电 电流	Maximum Discharge Current 最大放电 电流	Maximum Charge Voltage 最大充电 电压	Cut-Off Voltage 放电截 至电压
	(mAh)	(V)	(mA)	(mA)	(mA)	(mA)	(V)	(V)
Component	cell 组成申	电芯		*				
INR18650- 35E	3400	3.6	1700	680	2000	8000	4.2	2.5
Battery 电池								
P1089503- 003	3400	7.2	1000	680	1500	5000	8.4	5.0

Remark 备注:



	T	est Conclusion 测试结论	n	
Clause 条款	Test item 测试项目	Test Sample 测试样品	Test Result 测试结论	Remark 备注
38.3.4.1	Altitude simulation 高度模拟		Р	1
38.3.4.2	Thermal test 温度循环测试		Р	1
38.3.4.3 Vibration 振动		B1#-B8#	Р	1
38.3.4.4 Shock 冲击			Р	1
38.3.4.5	External short circuit 外部短路		Р	/
20.2.4.2	Impact 重物冲击	C1#-C10#	Р	1
38.3.4.6	Crush 挤压		N/A	1
38.3.4.7	Overcharge 过充电	B9#-B16#	Р	1
38.3.4.8	Forced discharge 强制放电	C21#-C40#	Р	1
Remark /		THE STATE OF		
	ass,合格;F表示 Failed,失败	1001/-X-	VON/ICO	
Test Envir 试验环境组	ronment Condition:	Amb	pient Temperature: 20± 5 环境温度: 20 ± 5°C	5°C
Test Date: 测试日期 2019.09.11 - 2019.09.27				

Test conclusion:

测试日期

The Rechargeable Li-ion Battery Packs submitted by TWS Technology (Guangzhou) Limited have passed the test items of UNITED NATIONS" Recommendations on the Transport of Dangerous Goods, Manual of Test and Criteria ST/SG/AC.10/11/Rev.6, amend1, section 38.3. 测试结论:

由广州明美新能源有限公司送检的可充式锂离子电池组符合联合国《关于危险品货物运输的建议书试验和标准手册》ST/SG/AC.10/11/Rev.6,amend1,section 38.3 的要求。

MCM Jechnology & Service

Report No.: GZLS20190911U01

UN Manual of Tests and Criteria ST/SG/AC.10/11/Rev.6, amend1, section 38.3. 联合国《关于危险货物运输的建议书试验和标准手册》ST/SG/AC.10/11/Rev.6, amend1, section 38.3. Clause Requirements Result Verdict

38.3.1	Scope 范围		P
	This section presents the procedures to be followed for the classification of lithium metal and lithium ion cells and batteries (see UN Nos 3090, 3091, 3480 and 3481, and the applicable special provisions of Chapter 3.3 of the Model Regulations. 本节介绍了锂金属/离子电芯/电池分类(见 UN3090、3091、3480 和 3481)应遵循《规章范本》第 3.3 章适用的特殊条款。		Р
38.3.3	When a cell or battery type is to be under this sub-section. The number and condition of cell and batteries of each type to be tested are as follows test item. 当一个电芯或电池型号须根据本分节进行试验时,试验的每个型号电芯和电池的数量和条件如测试项所示。	Shown as below 如下所示	P
	Sample quality 样品质量	Approx 133g	_
	Large/small cell/battery 大/小 电芯/电池	Small battery 小电池	_
38.3.3(f)	When testing a battery assembly in which the aggregate lithium content of all anodes when fully charged, is not more than 500 g, or in the case of a lithium battery, with a Watt-hour rating of not more than 6 200Wh, that is assembled from batteries that have passed all applicable tests, one assembled battery in a fully charged state shall be tested under tests T3, T4 and T5, and in addition, test T7 in the case of a rechargeable battery. 对于在完全充电时所有阳极的总锂含量不超过 500g,或额定功率不超过 6200Wh 的锂电池组(其由通过所有适用测试的电池组成),应对一个完全充电/满电状态的电池组加测 T3、T4和T5,另外,如果是可充电电池,则还需加测 T7。		N/A
38.3.3(g)	When batteries that have passed all applicable tests are electrically connected to form battery in which the aggregate lithium content of all anodes, when fully charged more than 500g, or in the case of a lithium ion battery, with a Watt-hour rating of more than 6 200Wh, the assembled battery does not need to be tested if the assembled battery is of a type that has been verified as preventing: - Overcharge; - Short circuits; and - Over discharge between the batteries 对于在完全充电时所有阳极的总理含量超过 500g,或额定功率超过 6200Wh 的锂电池组(其由通过所有适用测试的电池组成),当存在一种保护可以预防以下情况发生时,可以不需要进行加测: - 过充: - 短路; 且 - 电池之间的过放	ce	N/A



UN Manual of Tests and Criteria ST/SG/AC.10/11/Rev.6, amend1, section 38.3. 联合国《关于危险货物运输的建议书试验和标准手册》ST/SG/AC.10/11/Rev.6, amend1, section 38.3. Clause Requirements Result Verdict

38.3.4.1	Altitude simulation 高度模拟		
	Test simples shall be stored at a pressure of 11.6kPa or less for at least six hour at ambient temperature (20±5℃). 试验电芯和电池在环境温度(20±5℃)下,储存在小于等于11.6kPa 的压力下至少 6 小时。		Р
	Results: no leakage, no venting, no disassembly, no rupture, no fire, and the open circuit voltage drop not less than 90%. The requirement relating to voltage is not applicable to test cells and batteries at fully discharge states. 试验结果: 无泄漏、无排气、无解体、无破裂、无着火和开路电压降不低于 90%。测试电压的要求不适用于完全放电的电芯和电池。	See the TABLE: 38.3.4.1	Р
38.3.4.2	Thermal test 温度试验		Р
	Test cells and batteries are to be stored for at least six hours at a test temperature equal to $72\pm2^{\circ}$ C, followed by storage for at least six hours at a test temperature equal to $-40\pm2^{\circ}$ C, The maximum time interval between test temperature extremes is 30 minutes, This procedure is to be repeated until 10 total cycles are complete, after which all test cells and batteries are to be stored for 24 hours at ambient temperature ($20\pm5^{\circ}$ C). For large cells and batteries the duration of exposure to the test temperature extremes should be at least 12hours 将电芯和电池在温度为 $72\pm2^{\circ}$ C 的条件下贮存不少于 6 个小时,然后,在温度-40±2°C 条件下贮存不少于 6 个小时,然后,在温度-40±2°C 条件下贮存不少于 6 个小时,然后,在温度为 $20\pm5^{\circ}$ C 的条件下放置 24 个小时。大电芯和电池储存时间至少 12 h。	Stored for 6h at 72±2℃ and -40 ±2℃	Р
	Results: no leakage, no venting, no disassembly, no rupture, no fire, and the open circuit voltage drop not less than 90%. The requirement relating to voltage is not applicable to test cells and batteries at fully discharge states. 试验结果: 无泄漏、无排气、无解体、无破裂、无着火和开路电压降不低于 90%。测试电压的要求不适用于完全放电的电芯和电池。	See the TABLE: 38.3.4.2	Р
	侧风电压的安水小坦用了元王放电的电心和电池。	1	



Clause	Requirements	Result	Verdict
	Cells and batteries firmly secured to the platform of the vibration machine without distorting the cells in such a manner as to faithfully transmit the vibration. The vibration shall be a sinusoidal wave form with a logarithmic sweep between 7 Hz and 200 Hz and back to 7 Hz traversed in 15 minutes. This cycle shall be repeated 12 times for a total of 3 hours for each of three mutually perpendicular mounting positions of the cell. One of the directions of vibration must be perpendicular to the terminal face. 电芯和电池牢固地固定在振动机器的平台上,而不会使电芯变形,从而如实地传递振动。振动以正弦波形式进行,在 7Hz 和 200Hz 之间进行对数扫描,并在 15 分钟内返回至 7Hz。每个电芯和电池从三个互相垂直的方向上循环 12 次,3 个小时。振动方向之一必须垂直于终端面。		Р
	For cells and small batteries: from 7 Hz a peak acceleration of 1gn is maintained until 18 Hz reached. The amplitude is then maintained at 0.8mm (1.6mm total excursion) and the frequency increased until a peak acceleration of 8gn occurs (approximately 50Hz). A peak acceleration of 8gn is then maintained until the frequency is increased to 200Hz. 对于电芯和小电池: 保持峰值加速度 1gn,从 7Hz 到 18Hz。然后振幅保持在 0.8mm(总偏移量为 1.6mm),增加频率,直到峰值加速度达到 8gn(约 50Hz)。然后保持 8gn 的峰值加速度,直到频率增加到 200Hz。		Р
	For large batteries: from 7 Hz to a peak acceleration of 1gn is maintained until 18 Hz reached. The amplitude is then maintained at 0.8 mm (1.6 mm total excursion) and the frequency increased until a peak acceleration of 2gn occurs (approximately 25 HZ), A peak acceleration of 2gn is then maintained until the frequency is increased to 200 Hz. 对于大电池: 保持峰值加速度 1gn,从 7Hz 到 18Hz。然后振幅保持在 0.8mm(总偏移量为 1.6mm),增加频率,直到峰值加速度达到 2gn(约 25Hz)。然后保持 2gn 的峰值加速度,直到频率增加到 200Hz。	ce	N/A
	Results: no leakage, no venting, no disassembly, no rupture, no fire, and the open circuit voltage drop not less than 90%. The requirement relating to voltage is not applicable to test cells and batteries at fully discharge states. 试验结果: 无泄漏、无排气、无解体、无破裂、无着火和开路电压降不低于 90%。测试电压的要求不适用于完全放电的电芯和电池。	See the TABLE: 38.3.4.3	Р
38.3.4.4	Shock 冲击		Р
	Test cells and batteries shall be secured to the testing machine by means of a rigid mount which will support all mounting surfaces of each test battery. 试验电芯和电池应通过刚性支架固定在试验机上,该支架将支撑每个试验电池的所有安装面。		Р

Clause		Reg	quirements	Result	Verdic	
	accelerate Alternative of peak a millisecon 每个电芯 击。或者	ch cell shall be subjected to a half-sine shock of peak celeration of 150gn and pulse duration of 6 milliseconds. ernatively, large cells may be subjected to a half-sine shock ceak acceleration of 50gn and pulse duration of 11 liseconds. 个电芯应承受峰值加速度为 150gn、脉宽为 6 毫秒的半正弦冲。或者,大电芯可能受到峰值加速度为 50gn、脉宽为 11 毫秒半正弦冲击。 ch battery shall be subjected to a half-sine shock of peak celeration depending on the mass of the battery. The pulse ration shall be 6 milliseconds for small batteries and 11 liseconds for large batteries. The formulas below are wided to calculate the appropriate minimum peak celerations 个电池应承受的峰值加速度取决于电池的质量。小电池的脉宽内 6 毫秒,大电池的脉宽应为 11 毫秒。以下公式用于计算适的最小峰值加速度。				
	accelerate duration sillisecon provided accelerate 每个电池					
		Battery	Minimum peak acceleration	Pulse duration	7	
		Small batteries	150 g _n or result of formula $Acceleration(g_n) = \sqrt{\frac{100850}{mass^a}}$	6 ms		
			whichever is smaller			
		Large batteries	$50 \text{ g}_n \text{ or result of formula}$ $Acceleration(g_n) = \sqrt{\frac{30000}{mass^a}}$ whichever is smaller	11 ms		
		a Mass is expressed	in kilograms.		J	
	positive of each of th cell or ba 每一个电	or battery shall be direction and to thre hree mutually perpet ttery for a total of 1	subjected to three shocks in the se shocks in the negative direction in endicular mounting positions of the 8 shocks. 置的 3 个垂直的轴向的正方向和负方		Р	
	fire, and fire, and fire required and batter 试验结果	the open circuit volt irement relating to eries at fully dischar :无泄漏、无排气、 于 90%。	ting, no disassembly, no rupture, no tage drop not less than 90%. voltage is not applicable to test cells ge states. 、无解体、无破裂、无着火和开路电	See the TABLE: 38.3.4.4	Р	
				L		



Clause	Requirements	Result	Verdict
	The cell or battery to be tested shall be heated for a period of time necessary to reach a homogeneous stabilized temperature of 57±4°C, measured on the external case. This period of time depends on the size and design of the cell or battery and should be assessed and documented. If this assessment is not feasible, the exposure time shall be at least 6 hours for small cells and small batteries, and 12 hours for large cells and large batteries. Then the cell or battery at 57± 4°C shall be subjected to one short circuit condition with a total external resistance of less than 0.1 ohm. 待测电芯或电池应加热一段时间,以稳定均衡在 57±4°C 的温度,并测量外壳上的温度。加热时间取决于电芯或电池的尺寸和设计,应进行评估和记录: 如果评估不可行,小电芯或小电池的暴露/加热时间应至少为 6 小时,大电芯或大电池的暴露/加		Р
	热时间应至少为 12 小时。然后,在 57±4°C 下的电芯或电池应经受一次短路,总外部电阻小于 0.1 欧姆。 This short circuit condition is continued for at least one hour after the cell or battery external case temperature has returned to 57±4°C, or in the case of the large batteries, has decreased by half of the maximum temperature increase observed during the test and remains below that value. 在电芯或电池外部外壳温度恢复到 57±4°C 后,短路状态继续持续至少一小时,或对于大电池的情况下,降低至试验期间观察到的最大温升的一半,并保持在该值以下。		Р
	The short circuit and cooling down phases shall be conducted at least at ambient temperature. 短路和冷却阶段应至少在环境温度下进行。		Р
	WILLIIII SIX HOURS AREI THE LEST.	See the TABLE: 38.3.4.5	Р
38.3.4.6	Test T.6: Impact 重物冲击/Crush 挤压		P
38.3.4.6.2	Impact 重物冲击		Р
	Applicable to cylindrical cells not less than 18.0 mm in diameter 适用于直径不小于 18.0 mm 的圆柱型电芯		_



Clause	Requirements	Result	Verdict
	The test cell is placed on a flat smooth surface. A stainless steel bar (type 316 or equivalent) (Ø 15.8 mm ±0.1mm, length: ≥60 mm or of the longest dimension of the cell, whichever is greater) is placed across the centre of the test sample. A mass of 9.1 kg ±0.1 kg is dropped from a height of 61cm± 2.5cm at the intersection of the bar and the test sample in a controlled manner using a near frictionless, vertical sliding track or channel with minimal drag on the falling mass. The vertical track or channel used to guide the falling mass shall be oriented 90 degrees from the horizontal supporting surface. 测试电芯被放置平坦表面上。一根直径为 15.8± 0.1 毫米,长度至少 6 厘米(或该电芯的最大尺寸,以较大者为准)的 316 型不锈钢棒横放在样品的中心。一个重达 9.1 ± 0.1 千克的铁锤从 61±2.5 厘米高处以几乎无摩擦和零拉力的姿态沿垂直轨道或通道跌落至不锈钢棒与样品的交结点上。用以引导跌落的垂直轨道或通道或通道应与水平支撑面形 90°。		Р
,	The test sample is to be impacted with its longitudinal axis parallel to the flat surface and perpendicular to the longitudinal axis of the steel bar lying across the centre of the test sample. Each sample is to be subjected to only a single impact 被撞击的测试样品的长轴平行于平面,并与横放在样品中心的不锈钢棒垂直,每只样品只经受一次撞击。		Р
38.3.4.6.3	AND APPENDIX MADE AND APPENDIX		N/A
	Applicable to prismatic, pouch, coin/button cells and cylindrical cells lemm in diameter 适用于棱柱形、袋形、硬币/纽扣式电池和直径小于 18.0 mm 的圆柱型	1	_
	A cell or component cell is to be crushed between two flat surfaces. The crushing is to be gradual with a speed of approximately 1.5cm/s at the first point of contact. 在两个平面间对电芯或元件电芯进行挤压,挤压在第一个接触点的速度约为 1.5cm/s。	e	N/A
	The crushing is to be continued until the first of the three options below is reached. (a) The applied force reaches 13kN±0.78kN; (b) The voltage of the cell drops by at least 100 mV; or (c) The cell is deformed by 50% or more of its original thickness. Once the maximum pressure has been obtained, the voltage drops by 100mV or more, or the cell is deformed by at least 50% of its original thickness, the pressure shall be released. 直到发生下述三个条件中的任一条件: (a) 作用力达到 13kN±0.78kN: (b) 电芯电压下降至少 100mV; 或 (c) 电芯厚度和最初比较变形 50%以上。 一旦达到最大压力,电压降超过 100 mV 或者电芯变形至少50%,压力应该解除。		N/A



Clause	Requirements	Result	Verdict	
	A prismatic or pouch cell shall be crushed by applying the force to the widest side. A button/coin cell shall be crushed by applying the force on its flat surface. For cylindrical cells, the crush force shall be applied perpendicular to longitudinal axis. 校形或袋装电芯应该在宽面施加挤压力,纽扣/硬币电芯应该在平面施加挤压力。圆柱型电芯应该在长轴的垂直方向施加挤压力。		N/A	
	Each test cell or component cell is to be subjected to one crushed only. The test sample shall be observed for a further 6h. The test shall be conducted using test cell or component cells that have not previously been subjected to others tests. 每一个测试的电芯或元件电芯只进行一次挤压,测试后再观察6h. 用于测试的电芯或元件电芯之前没有进行过其它的测试。		N/A	
38.3.4.6.4	Result of Impact/Crush 重物冲击/挤压的结论		Р	
	Results: External temperature does not exceed 170°C and there is no disassembly and no fire during the test and within six hours after this test 试验结果: 外部温度不超过 170°C,试验期间和试验后 6 小时内,无解体或起火现象。	See the TABLE: 38.3.4.6	Р	
38.3.4.7	Overcharge 过充电			
	Applicable to rechargeable lithium cell/battery with overcharge pr 适用于具有过充电保护功能的可充电锂电芯/电池。	otection.	_	
	The charge current shall be twice the manufacturers' recommended maximum continuous charge current. 充电电流应为制造商推荐的最大持续充电电流的两倍。		Р	
	The minimum voltage of the test shall be as follows. 试验的最小电压如下。	се	Р	
	-When the manufacturer's recommended charge voltage is not more than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage of the battery or 22V. 制造商建议的充电电压不大于 18 伏时,实验的最小电压应是电池组最大充电电压的两倍或 22 伏两者中的较小者。		Р	
	When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times maximum charge voltage. 制造商建议的充电电压大于 18 伏时,实验的最小电压应是最大充电电压的 1.2 倍。		N/A	
	Tests are to be at ambient temperature. The duration of the test shall be 24 hours		Р	
	测试在室温下进行,测试时间为 24h. Results: there is no disassembly and no fire during the test and within seven days after this test 试验结果: 试验期间和试验后 7 天内,无解体或起火现象。	See the TABLE: 38.3.4.7	Р	
38.3.4.8	Forced discharge 强制放电		Р	



UN Manual of Tests and Criteria ST/SG/AC.10/11/Rev.6, amend1, section 38.3. 联合国《关于危险货物运输的建议书试验和标准手册》ST/SG/AC.10/11/Rev.6, amend1, section 38.3.

Clause	Requirements	Result	Verdict	
	Each cell shall be forced discharged at ambient temperature by connecting it in series with a 12V D.C, power supply at an initial current equal to the maximum discharge current specified by the manufacturer.			
	在环境温度下,将单个电芯连接在 12V 的直流电源上进行强制放电,此直流电源提供给每个电芯的初始电流为制造厂指定的最大放电电流。			
	The specified discharge current is to be obtained by connecting a resistive load of the appropriate size and rating in series with the test cell, Each cell shall be forced discharged for a time interval (in hours) equal to its rated capacity divided by the initial test current (in ampere).		Р	
	规定的放电电流通过适当大小的阻性电子负载与电芯串联获得,电芯强制放电的时间为额定容量除以初始电流。	,1		
	Results: there is no disassembly and no fire during the test and within seven days after this test 试验结果: 试验期间和试验后 7 天,无解体或起火现象。	See the TABLE: 38.3.4.8	Р	



RF: UN38.3 Rev.6 amend1 02



ABLE: 38.3.4.1 Altitude simulation 高度模拟						Pass	
MODEL	Before test		After test		Mass loss	Residual	
	Mass(g)	OCV(V)	Mass(g)	OCV(V)	(%)	OCV (%)	Results
			Fully charged	at first cycle			
B1#	132.883	8.33	132.882	8.32	0.001	99.88	Pass
B2#	133.138	8.32	133.136	8.32	0.002	100.00	Pass
B3#	132.899	8.32	132.898	8.32	0.001	100.00	Pass
B4#	133.105	8.33	133.104	8.32	0.001	99.88	Pass
			Fully charged	after 25 cycle	es		
B5#	132.939	8.32	132.939	8.31	0.000	99.88	Pass
B6#	132.790	8.33	132.789	8.32	0.001	99.88	Pass
B7#	132.966	8.32	132.964	8.31	0.002	99.88	Pass
B8#	133.067	8.32	133.065	8.31	0.002	99.88	Pass

Results: Pass = no leakage, no venting, no disassembly, no rupture, no fire, and the open circuit voltage drop not less than 90%

ABLE: 38.3	3.4.2 Thermal	test 温度试验					Pass
MODEL	Before test		After test		Mass loss	Residual	
	Mass(g)	OCV(V)	Mass(g)	OCV(V)	(%)	OCV (%)	Results
	bihi i		Fully charged	at first cycle			
B1#	132.882	8.32	132.868	8.22	0.011	98.80	Pass
B2#	133.136	8.32	133.126	8.21	0.008	98.68	Pass
B3#	132.898	8.32	132.882	8.22	C0.012	98.80	Pass
B4#	133.104	8.32	133.089	8.21	0.011	98.68	Pass
			Fully charged	after 25 cycle	es		
B5#	132.939	8.31	132.922	8.21	0.013	98.80	Pass
B6#	132.789	8.32	132.775	8.22	0.011	98.80	Pass
B7#	132.964	8.31	132.948	8.21	0.012	98.80	Pass
B8#	133.065	8.31	133.051	8.20	0.011	98.68	Pass

Results: Pass = no leakage, no venting, no disassembly, no rupture, no fire, and the open circuit voltage drop not less than 90%



ABLE: 38.3.4.3 Vibration 振动						Pass	
MODEL	Before test		After test		Mass loss	Residual	
	Mass(g)	OCV(V)	Mass(g)	OCV(V)	(%)	OCV (%)	Results
			Fully charged	at first cycle			
B1#	132.868	8.22	132.867	8.20	0.001	99.76	Pass
B2#	133.126	8.21	133.125	8.19	0.001	99.76	Pass
B3#	132.882	8.22	132.880	8.21	0.002	99.88	Pass
B4#	133.089	8.21	133.088	8.20	0.001	99.88	Pass
			Fully charged	after 25 cycle	es		
B5#	132.922	8.21	132.921	8.20	0.001	99.88	Pass
B6#	132.775	8.22	132.773	8.20	0.002	99.76	Pass
B7#	132.948	8.21	132.946	8.19	0.002	99.76	Pass
B8#	133.051	8.20	133.050	8.19	0.001	99.88	Pass

Results: Pass = no leakage, no venting, no disassembly, no rupture, no fire, and the open circuit voltage drop not less than 90%

ABLE: 38.3	3.4.4 Shock 冲	击					Pass
MODEL	Before test		After test		Mass loss	Residual	
	Mass(g)	OCV(V)	Mass(g)	OCV(V)	(%)	OCV (%)	Results
1 1 11			Fully charged	at first cycle			
B1#	132.867	8.20	132.867	8.20	0.000	100.00	Pass
B2#	133.125	8.19	133.124	8.19	0.001	100.00	Pass
B3#	132.880	8.21	132.879	8.21	0.001	100.00	Pass
B4#	133.088	8.20	133.088	8.20	0.000	100.00	Pass
			Fully charged a	after 25 cycle	s		
B5#	132.921	8.20	132.921	8.20	0.000	100.00	Pass
B6#	132.773	8.20	132.772	8.20	0.001	100.00	Pass
B7#	132.946	8.19	132.946	8.19	0.000	100.00	Pass
B8#	133.050	8.19	133.050	8.19	0.000	100.00	Pass

Results: Pass = no leakage, no venting, no disassembly, no rupture, no fire, and the open circuit voltage drop not less than 90%



ABLE: 38.3.4.5 External Short-circuit 外部短路					
MODEL	Ambient(°C) (At 57± 4°C)	Testing resistance (mΩ)	Max. External Temperature(°C)	Results	
		Fully charged at first cycle			
B1#	57.0	83.2	57.4	Pass	
B2#	57.0	82.7	57.6	Pass	
B3#	57.0	83.6	57.3	Pass	
B4#	57.0	84.0	57.6	Pass	
		Fully charged after 25 cycles			
B5#	57.1	83.9	57.3	Pass	
B6#	57.1	83.6	57.6	Pass	
B7#	57.1	82.4	57.6	Pass	
B8#	57.1	83.2	57.4	Pass	

4.6 Impact 重物冲击				Pass
TABLE: 38.3.4.6 Crush 挤压				
Max. External Temperature(°C)	Results	MODEL	Max. External Temperature(°C)	Results
design rated capacity at	first cycle	50% of the	design rated capacity after	er 25 cycles
26.9	Pass	C6#	24.9	Pass
25.9	Pass	C7#	25.5	Pass
25.4	Pass	C8#	⊖r∨ 36,6 -	Pass
25.7	Pass	C9#	28.7	Pass
33.1	Pass	C10#	29.2	Pass
	Max. External Temperature(°C) design rated capacity at 26.9 25.9 25.4 25.7	Max. External Temperature(°C) design rated capacity at first cycle 26.9 Pass 25.9 Pass 25.4 Pass 25.7 Pass	Max. External Temperature(°C) design rated capacity at first cycle 26.9 25.9 Pass C6# 25.4 Pass C8# 25.7 Pass C9#	Max. External Temperature(°C) design rated capacity at first cycle 26.9 Pass C6# 25.9 Pass C7# 25.5 25.4 Pass C8# C9# 28.7


TABLE: 38.3.4.7 Overcharge 过度充电					Pass	
The test current = 3.0A The test voltage = 16.8V						
						MODEL OCV(V) Results MODEL OCV(V)
Fu	lly charged at first cy	rcle	Full	y charged after 25 cy	cles	
B9#	8.33	Pass	B13#	8.33	Pass	
B10#	8.32	Pass	B14#	8.32	Pass	
B11#	8.33	Pass	B15#	8.32	Pass	
B12#	8.33	Pass	B16#	8.32	Pass	



ABLE: 38.3.4.8 Forced discharge 强制放电					
MODEL	OCV(V)	Results	MODEL	OCV(V)	Results
Fully	discharged at first of	cycle	Fully	discharged after 25 d	cycles
C11#	3.292	Pass	C21#	3.287	Pass
C12#	3.301	Pass	C22#	3.306	Pass
C13#	3.299	Pass	C23#	3.288	Pass
C14#	3.285	Pass	C24#	3.294	Pass
C15#	3.287	Pass	C25#	3.301	Pass
C16#	3.296	Pass	C26#	3.306	Pass
C17#	3.300	Pass	C27#	3.304	Pass
C18#	3.287	Pass	C28#	3.288	Pass
C19#	3.296	Pass	C29#	3.293	Pass
C20#	3.304	Pass	C30#	3.302	Pass













注意事项 Important

1. 本报告无检验单位公章、骑缝章无效;

The test report is invalid without the official stamp and Paging seal of Guangzhou MCM Certification and Testing Co., Ltd.

2. 未经本试验室书面同意,不得部分地复制本报告。

Nobody is allowed to photocopy or partly photocopy this test report without written permission of Guangzhou MCM Certification & Testing Co., Ltd..

3. 本报告无批准人、审核人及检测人签名无效。

The test report is invalid without the signatures of Approver, Checker and Tester.

4. 本报告涂改无效。

The test report is invalid if altered.

- 5. 对检验报告若有异议,应于收到报告之日起十五天内向检验单位提出。 Objections to the test report must be submitted to Guangzhou MCM Certification & Testing Co., Ltd. within 15 days.
- 6. 本报告仅对来样负责。

The test report is valid for the tested samples only.

检测单位:广州邦禾检测技术有限公司

Laboratory: Guangzhou MCM Certification & Testing Co., Ltd.

地 址: 中国广州市番禺区市广路钟三路段 13 号之一

Address: 1 F No.13, Zhong San Section, ShiGuang Road, Panyu District, Guangzhou City,

Guangdong Province, China.

0086-20-34777663 **Web**: <u>Http://www.mcmtek.com</u>